

## SPECIFICATION

|                    |          |                                      |
|--------------------|----------|--------------------------------------|
| Quality            |          | : <b>BOULDER</b>                     |
| Product definition |          | : Colour Placement Loop tufting      |
| Gauge              |          | : 1/10"                              |
| No. of tufts       | ISO 1763 | : ± 36 stitches/10cm stitch rate     |
| Pile fibre         |          | : 100% solution dyed nylon           |
| Pile weight        | ISO 8543 | : 710 gr/m <sup>2</sup> ± 5%         |
| Pile height        | ISO 1766 | : 2-4 mm ± 5%                        |
| Primary backing    |          | : PET woven - ± 150gr/m <sup>2</sup> |
| Tile backing       |          | : Polyflex                           |
| Total thickness    | ISO 1765 | : 6.50 mm ± 5%                       |
| Total weight       | ISO 8543 | : 4800 gr/m <sup>2</sup> ± 7,5%      |
| Tile size          |          | : 50 x 50 cm (± 19.7" x 19.7")       |
| Tiles per box      |          | : 20                                 |

## PERFORMANCE

|                       |                   |                            |
|-----------------------|-------------------|----------------------------|
| Use classification    | method en 1307    | : 33                       |
| Castor chair test     | EN 985            | : A, continuous use        |
| Abrasion              | ISO 12951         | : pass                     |
| Vettermann test       | ISO 10361/EN 1471 | : pass                     |
| Thermal isolation     | ISO 8302          | : 0.088 m <sup>2</sup> K/W |
| Dimensional stability | EN 986            | : pass                     |
| Luxury/Comfort        | EN 1307           | : classe 1                 |
| Sound Absorption      | ISO 140-8         | : 24 dB                    |

## ELECTROSTATIC PROPERTIES

|                                  |              |                        |
|----------------------------------|--------------|------------------------|
| Walk on test                     | ISO 6356     | : < 2.0 kV             |
| Horizontal electrical resistance | ISO CD 10965 | : 3x10 <sup>8</sup> Ω  |
| Vertical electrical resistance   | ISO CD 10965 | : 4x10 <sup>10</sup> Ω |
| Static loading                   |              | : anti-static          |

## FLAME PROPERTIES

|                    |                |                        |
|--------------------|----------------|------------------------|
| Reaction to fire   | EN ISO 11925-2 |                        |
|                    | EN ISO 9239-1  | : B <sub>fl</sub> - s1 |
| Hot metal nut test | BS 4790        | : Low Radius           |

## COLOUR FASTNESS PROPERTIES

|              |             |       |
|--------------|-------------|-------|
| Light        | ISO 105 B02 | : > 5 |
| Rubbing, dry | ISO 105 X12 | : 4.5 |
| Rubbing, wet | ISO 105 X12 | : 5.0 |
| Shampoo      | BS 1006     | : 4.5 |
| Water        | ISO 105 E01 | : 4.5 |
| Water stains | TNO W 6024  | : 5.0 |



## GENERAL

Recommended maintenance:  
Pile direction:

Best results are obtained when cleaned with a dry shampoo method.  
Directional arrows are printed on the back of each tile.  
Best results are obtained when laid checkerboard.

Laying instructions:

Tiles require no underlay, nailing, gluing or sewing and may be laid loose on a flat, dry, non-slippery floor. When tiles are laid on parquet, vinyl or in open areas larger than 30 m<sup>2</sup> it is advisable to use double sided adhesive tape on every 8th row or a tackifier.

## COLOURS

|                  |                   |
|------------------|-------------------|
| 003<br>Antracite | 015<br>Light Grey |
| 006<br>Blue/Grey | 007<br>Earth      |

|                   |                     |
|-------------------|---------------------|
| 008<br>Dark Brown | 016<br>Brown        |
| 201<br>Sand       | 010<br>Dark grey    |
| Felt<br>Backing   | Polyflex<br>Backing |